

# TEST REPORT

Test Report No. 70.405.20.13797.01R1  
Dated 2020-05-14



ORIGINAL

Applicant:  
Address:

Attn:

Order No.:  
Style No.: Universal  
Season: All Seasons  
No. of samples:  
Buyer:  
Country of Origin: China  
Goods Export To: USA

Care Label Provided:

Receipt Date of Sample: Received on 2020-05-13  
Date of Testing: From 2020-05-13 To 2020-05-13  
Sample Submitted: The sample(s) was (were) submitted by applicant and identified.  
The product's function is declared by the applicant.  
The testing point(s) was (were) selected by the applicant.  
Test Result: Refer to Next Page.

TÜV SÜD Certification and Testing (China) Co., Ltd. Shanghai Branch  
Testing Center  
Prepared by:

Andy Wang  
Softlines Department

Authorized by:

Sherry Wang  
Softlines Department

- Note: (1) The TÜV SÜD Certification and Testing (China) Co., Ltd. "General Terms & Conditions" applied.  
For full version, please visit: <http://www.tuv-sud.cn/cn-scn/terms-and-conditions>  
(2) The results relate only to the items tested, (3) The test report shall not be reproduced except in full without the written approval of the laboratory.  
(4) Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

Laboratory:  
TÜV SÜD Certification and Testing  
(China) Co., Ltd. Shanghai Branch  
Testing Center Softlines Lab

Phone: +86 21 6037 6300  
Fax: +86 21 6037 6350  
E-mail: [softlines@tuv-sud.cn](mailto:softlines@tuv-sud.cn)  
[www.tuv-sud.cn/softlines](http://www.tuv-sud.cn/softlines)

Regd. Office:  
TÜV SÜD Certification and Testing (China) Co., Ltd. Shanghai  
Branch Testing Center Softlines Lab  
2F Building B, No. 1999 Du Hui Rd, Minhang District, Shanghai  
201108 P.R. China

Page 1 of 2


# TEST REPORT

Test Report No. 70.405.20.13797.01R1  
Dated 2020-05-14



ORIGINAL

## Description of The Test Subject

Sample	Description	Photo
001	PE Gown in blue for waterproof and anti-static	

## Test Results

- Water Resistance-Impact Penetration Test**  
AATCC 42:2017e  
Weight of blotter gained(g)  
**001-Front panel**  
0.0
- Hydrostatic head Test**  
AATCC 127:2017(2018)e Option 2; Hydrostatic Head; Rate Of Increase Of Water Pressure: 60cm/min.,  
Face Side Facing Water  
**As Received**  
(cm.H<sub>2</sub>O)  
**001-Front panel**  
76.5

Remark: This Report is to Supersede Test Report No.70.405.20.13797.01 Issued on 2020-05-13.

-End of The Test Report-

TEST REPORT

Applicant :

Date : May 14, 2020

Sample Description As Declared :

No. Of Sample : One  
Fibre Content : -  
Material : DISPOSABLE PLASTIC PE GOWN : -  
Finishing : -  
End Uses : BLUE  
Colour : UNISEX  
Style No.  
Order No./PO No. : PE GOWN  
Buyer's Name : -  
Manufacturer's Name : -  
Ref. : -

Applicant's Provided Care Instruction/Label :

-

Date Sample Received : May 13, 2020

Date Testing Started : May 13, 2020

---

Conclusion:

Impact Penetration Test As Received M  
Hydrostatic Pressure Test As Received M

Note : C = Conform Label M\* = Commercially Acceptable  
M = Meet Applicant's Requirement F\* = Fail  
F = Fail To Meet Applicant's Requirement N/A = Not Applicable  
# = No Comment

---

Prepared And Checked By:  
For Intertek Testing Services Wuxi Ltd.

*Rachel Lu*

---

Rachel Lu  
Textile Lab Manager

TEST REPORT

Tests Conducted (As Requested By The Applicant)

1 Water Resistance As Received -Impact Penetration Test Method (AATCC 42-2017):

	Test On Body Fabric	<u>Applicant's Requirement</u>
(Grams Of Water Absorbed)		
Specimen 1	Negligible	<=1.0g
Specimen 2	Negligible	
Specimen 3	Negligible	
Average	Negligible	

2 Hydrostatic Pressure Test As Received (AATCC 127-2018, Option 2, Hydrostatic Head Tester, Pressure Gradient At 60 mbar/min Water Pressure):

	Test On Body Fabric	<u>Applicant's Requirement</u>
Specimen 1	815 mm	>=200mm.H2o
Specimen 2	785 mm	
Specimen 3	770 mm	
Average	790 mm	

---

End of Report

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.*

*This report shall not be reproduced except in full, without written approval of the laboratory*